



1100-1190 West Hastings Street, Vancouver, B.C.V6E 3T5;Tel: 604-899-2515; Tel: 1-888-456-1112; Fax: 604-688-4670;

Email: corpdev@mnxlt.com; Website: www.fortuneriver.ca

**Table I:
FRX Significant Gold Assays- Drayton Property 2006**

Drill Hole No.	From metres	To metres	Interval metres	Orig. 1/2 split FA Au g/t	Duplicate 1/4 split FA Au g/t	Original Metallics Au g/t
DT06-01 and	30.2 47.9	40.8 57.0	10.6 9.1	1.3 0.9		0.5 1.0
DT06-02	107.7	114.4	6.8	0.8		pending
DT06-03	35.3	37.3	2.0	7.4	4.8	14.5
DT06-04	158.6	160.1	1.5	3.9		4.3
DT06-05	116.4	118.0	1.6	1.2		pending
DT06-06	65.9	68.1	2.2	1.9		1.1
DT06-10	87.3	91.1	3.8	1.0		pending

True Thickness not calculated due to limited structural data

Fire Assay: 50gr Au assay on 250 to 400gr pulp

Metallics Assay: 1000g screen sample sieved through 150 mesh. Entire +150 fraction assayed and duplicate -150 assays